

REMARKS

In view of the above amendments and the following remarks, reconsideration of the rejections contained in the Office Action of July 6, 2001, is respectfully requested.

In order to make necessary editorial corrections, the entire specification and abstract have been reviewed and revised. As the revisions are quite extensive, the amendments to the specification and abstract have been incorporated into the attached substitute specification and abstract. For the Examiner's convenience, a copy of the marked-up original specification and abstract is also enclosed, and the marked-up pages are captioned "Version with markings to show changes made". The substitute specification and abstract includes the same changes as are indicated in the marked-up copy of the original specification. No new matter has been added by the revisions. Entry of the substitute specification is thus respectfully requested.

The Examiner has rejected claims 1-3 as being unpatentable over the Zeller reference (USP 3,331,260) in view of the Nishibori reference (USP 4,505,869). However, as indicated above, original elected claims 1-3 and non-elected claims 4-14 have been cancelled and replaced with new claims 15-28, and all of the new claims are directed to the elected invention. For the reasons discussed below, it is respectfully submitted that new claims 15-28 are clearly patentable over the prior art as applied by the Examiner.

As recited in new independent claim 15, the steering wheel of the present invention comprises an annular rim section that includes arcuate rim elements mounted on a core. Each of the rim elements is formed of thermosoftening synthetic resin material blended with woodmeal so as to form an annular streak pattern on an outer surface of each of the rim elements.

As explained in the specification, steering wheels with wood rims are desirable but difficult to obtain. Thus, the present invention provides a steering wheel with an imitation wood angular rim section. As explained on page 13, line 27 through page 14, line 14, pellets of synthetic resin material and woodmeal are fed into an extruding machine to form the arcuate rim element of the present invention. Due to the different textures and colors of the pellets, an annular streak pattern is formed on the outer surface of each of the extruded rim elements. As a result, each of the rim elements

exhibit a woodgrain appearance, even if the surface of the rim elements is notched, sanded, or otherwise treated to produce a surface contour.

The Zeller reference discloses a steering wheel with a wood-surfaced ring including a lower veneer 4 and a top veneer 5. The Examiner acknowledges that this reference fails to show a rim section made of thermosoftening synthetic resin with woodmeal that creates a wooden flow pattern and a color pigment to show woodgrain. Nonetheless, the Examiner asserts that the Nishibori reference discloses a rim section formed of thermosoftening synthetic resin and woodmeal, resulting in a flow pattern being formed.

The Nishibori reference discloses a urea resin being added to wood chips to form an aggregate, and the aggregate is then mixed with resin which is then molded into a desired form. However, this reference does not disclose or suggest that the rim elements are formed of thermosoftening synthetic resin material blended with woodmeal *so as to form an annular streak pattern on an outer surface of each of the rim elements*. It is submitted that simply adding woodmeal or wood chips into a resin material to be molded into a desired shape would not produce a annular streak pattern as recited in claim 15. Moreover, it is submitted that the Nishibori reference does not disclose or even suggest any such annular streak pattern. Therefore, one of ordinary skill in the art would not be motivated by the Nishibori reference to modify the Zeller reference so as to obtain the invention recited in independent claim 15. Accordingly, it is respectfully submitted that independent claim 15 and the claims that depend therefrom are clearly patentable over the prior art of record.


In view of the above amendments and remarks, it is submitted that the present application is now in condition for allowance, and the Examiner is requested to pass the case to issue. If the

Examiner should have any comments or suggestions to help speed the prosecution of this application,
the Examiner is requested to contact the Applicants' undersigned representative.

Respectfully submitted,

Jun TANABE et al.

By:

A handwritten signature in black ink, appearing to read 'W. Douglas Hahn', written over a horizontal line.

W. Douglas Hahn
Registration No. 44,142
Attorney for Applicants

WDH/pth
Washington, D.C. 20006-1021
Telephone (202) 721-8200
Facsimile (202) 721-8250
January 7, 2002



Version with Markings to
Show Changes Made

TITLE OF THE INVENTION

STEERING WHEEL AND METHOD FOR MANUFACTURING SAME

BACKGROUND OF THE INVENTION

5 This invention relates to a steering wheel for a vehicle, and more particularly to a steering wheel having both an appearance and feel of ~~wood like that of~~ natural wood and a method for manufacturing the same.

10 A steering wheel for a vehicle is ~~kept~~ grasped by a driver during driving of the vehicle. ~~Thus,~~ ^{It} is essential that the steering wheel not only exhibits a satisfactory appearance but is pleasant to the touch. Such pleasant touch means that the steering wheel does not exhibit an excessively smooth feel, a rough feel and a tacky feel. Also, it means that the steering
15 wheel is not slippery, excessively hot ^{OR} ~~and~~ excessively cold. Such requirements for the pleasant touch are sufficiently satisfied by a conventional wooden steering wheel.

Unfortunately, the wooden steering wheel ~~causes distortion~~ ^{formed of} ~~peculiar to a~~ natural tree material ^{MAY BECOME DISTORTED} due to a variation in ambient
20 temperature, irradiation of direct sun beams thereon, a variation in ambient moisture and the like. This results in peeling of the wooden steering wheel, cracking thereof and the like. Also, the wooden steering wheel is not suitable ^{for mass production} because currently a natural wood material is ^{DIFFICULT TO OBTAIN} ~~highly hard to be available~~.

25 In view of the above, a steering wheel which is constructed so as to have the feel of wood like that of natural wood has been recently substituted for the wooden steering wheel in the market. Such a substitute steering wheel is generally manufactured by forming a suitable synthetic resin material into
30 a rim section for the steering wheel by molding and applying the appearance of wood to the rim section. Such application of the appearance of wood is carried out ^{by} ~~using~~ either ~~techniques of~~ providing an appearance of the thus-formed rim section with the feel of wood or ~~techniques of~~ subjecting a synthetic resin

material which has woodmeal previously added thereto to injection molding to form a rim section. The latter techniques provide the steering wheel with not only the feel of wood but an appearance of wood due to a stream or flow pattern formed on the rim section during the injection molding.

5 However, the former techniques ¹⁵ are disadvantageous in that printing on the rim section carried out after the above-described molding fails to provide the steering wheel with a satisfactory feel of wood, although it provides the steering wheel with an appearance which is very similar to that of natural wood. Also, the latter techniques ¹⁰ of injection molding the synthetic resin material having the woodmeal added thereto fails to permit the steering wheel to exhibit a satisfactory appearance of wood although ¹¹ they provide it with an improved feel of wood. ¹⁵ More particularly, in the latter techniques, the flow pattern formed during the injection molding is excessively emphasized due to foaming of moisture held in the woodmeal. Also, the latter techniques cause discoloration of the woodmeal due to generation of heat from the woodmeal by high shearing. The flow pattern ²⁰ formed during the injection molding is principally based on a curved flow pattern formed by a phenomenon that synthetic resin materials injected from several gates freely flow in a mold cavity and then merge with each other. In other words, the curved flow pattern is formed by spreading of the synthetic resin materials from the gates and swirling of the materials in places. ²⁵ If such spreading and swirling of the synthetic resin materials permitted the curved flow pattern to be finely formed, the steering wheel would be provided with an appearance of high quality ³⁰ in imitation of precious wood which provides a pretty grain pattern of wood, such as a circular grain pattern, a grape-like grain pattern, or the like as seen in a zelkova tree, a mulberry tree, a camphor tree, a jujube tree or the like. Unfortunately, the techniques currently practiced fail to provide the steering wheel with the feeling of high-grade wood ³⁵ in an

OR APPEARANCE

~~appearance~~

SUMMARY OF THE INVENTION

The present invention has been made in view of the foregoing disadvantages of the prior art and as a result of the inventors' effort ^{to} ~~ed~~ developing a steering wheel which has both an appearance and feel ~~of wood~~ which is substantially equal to that of natural wood, and a method for manufacturing the same. In a steering wheel of the present invention, an appearance of wood which is substantially equal to or the same as that of natural wood does not refer to an appearance of precious wood having a pretty grain pattern of wood, such as a circular grain pattern, a grape-like grain pattern, or the like. Rather, it refers to a general woodgrain such as a straight grain or a cross grain. In the present invention, such a woodgrain is formed on a rim section of the steering wheel while defining a flow pattern in a circumferential direction of the rim section, to thereby give the impression that the flow pattern is formed by a sliced veneer.

Accordingly, it is an object of the present invention to provide a steering wheel which is capable of giving the impression that it ^{is} formed thereon with a woodgrain pattern ⁱⁿ ~~a manner to extend~~ in a circumferential direction thereof. ^{ING} ~~resulting in~~ the steering wheel ^{HAS} ~~having~~ both an appearance and feel of wood which is substantially equal to that of natural wood.

It is another object of the present invention to provide a method for manufacturing a steering wheel which is capable of ensuring reliable and inexpensive mass-production of a steering wheel which gives the impression that the steering wheel is ^{EXTENDING} ~~formed thereon with a woodgrain pattern in a manner to extend~~ in a circumferential direction thereof, resulting in the steering wheel having both an appearance and feel of wood which is substantially equal to that of natural wood.

In accordance with one aspect of the present invention, a

steering wheel is provided. The steering wheel includes a rim section having a core incorporated therein. The rim section is constituted by rim elements made of a thermosoftening synthetic resin material to which woodmeal is added, resulting in the rim section being formed thereon with a flow pattern. The rim elements are each re-shaped from a straight rod-like configuration into an arcuate configuration ^{TO CONFORM} ~~in conformity~~ to a curvature of the core, ^{ARE} ~~and~~ mounted on the core so that the flow pattern may be transformed into an annular flow pattern.

Such construction of the present invention permits the steering wheel to give the impression that the steering wheel is formed thereon with a woodgrain pattern ~~in a manner to extend~~ ^{EXTENDING} in a circumferential direction thereof, so that it may have both an appearance and feel of wood which is substantially equal to that of natural wood.

In a preferred embodiment of the present invention, the thermosoftening synthetic resin material has a color pigment added thereto so that the flow pattern is formed in an annular flow pattern which has a clear woodgrain emphasized by the color pigment added. Thus, the steering wheel of the embodiment of the present invention gives the strong impression that it is formed thereon with a woodgrain pattern as if it is formed by a sliced veneer.

In a preferred embodiment of the present invention, the rim section is formed thereon with ~~holding~~ unevenness in such a manner that the flow pattern is transformed into the annular flow pattern while preventing the thus-formed annular flow pattern from being ^{DISTORTED} ~~disordered~~ by the ~~holding~~ unevenness. Thus, the steering wheel of the embodiment of the present invention gives the strong impression that it is formed thereon with a woodgrain pattern as if the ~~holding~~ unevenness on the steering wheel is formed by cutting of natural wood.

In accordance with another aspect of the present invention, a method for manufacturing a steering wheel is

provided. The method includes the steps of extruding a thermosoftening synthetic resin to which woodmeal is added to prepare a pair of straight rod-like rim elements, bending the straight rod-like rim elements into an arcuate shape ~~in~~ ^{TO CONFORM} ~~conformity~~ to a curvature of a core while keeping the rim elements softened, and mounting the rim elements thus bent on the core while interposing the core therebetween.

Thus, the method permits mass-production of a steering wheel which gives the impression that it is formed thereon with a woodgrain pattern ~~in a manner to extend~~ ^{EXTENDING} in a circumferential direction thereof, resulting in the steering wheel having both an appearance and feel ~~of wood which is~~ substantially equal to that of natural wood.

In a preferred embodiment of the present invention, the extruding step is carried out using a nozzle formed to have a semicircular shape in section having an arc section formed substantially ~~in conformity~~ ^{CONFORM} to an arcuate shape which is a half of a sectional configuration of a rim section of a finished steering wheel and which is defined at an outermost portion of the rim section, and a chord section projectingly provided with a core corresponding section which is formed ^{TO} substantially ~~conformity~~ ^{CONFORM} to a half of a sectional configuration of the core, resulting in the rim elements being prepared in the form of a straight rod-like shape.

Such construction permits mounting of the rim elements on the core ~~to be carried out~~ in the subsequent step, to thereby prevent disorder ^(MISALIGNMENT) of the flow pattern in the circumferential or annular direction during re-shaping of the rim elements.

In a preferred embodiment of the present invention, the bending step is carried out using a regulating die formed thereon with projections for forming ~~holding~~ unevenness and a forcing die, wherein the straight rod-like rim elements are each softened by re-heating to be roughly bent into an arcuate shape and then fitted in the regulating die, then pressed by ~~means of~~ the

THE RIM ELEMENTS ARE

forcing die, during which the regulating die and forcing die--
cooperate with each other to define an arcuate cavity having a
room region defined at each ~~of~~ opposite ends thereof in a
longitudinal direction thereof. Thus, the method of the present
5 invention attains satisfactory re-shaping of the rim elements
while effectively preventing ~~disorder~~ of the flow pattern in the
circumferential direction. MISALIGNMENT

In a preferred embodiment of the present invention,
10 wherein the pair of rim elements each include a front side rim
element observable from a driver's seat (A FRONT SIDE OF THE STEERING WHEEL) and a rear side rim
element opposite to the front side rim element. The mounting
step is carried out by mounting the front and rear side rim
elements on the core while adhesively joining the front and rear
rim elements to each other.

15 Such construction permits joints between the front side
rim element and the rear side rim element to be positioned at an
outermost periphery of the rim section and an innermost periphery
thereof, so that the joints may be substantially out of sight of
a driver. Also, it permits mounting of the rim elements on the
20 core to be attained with increased strength.

In a preferred embodiment of the present invention, the
pair of rim elements each include an inner peripheral side rim
element and an outer peripheral side rim element opposite to the
front side rim element. The mounting step is carried out by
25 mounting the inner and outer peripheral side rim elements on the
core while adhesively joining the inner and outer peripheral side
rim elements to each other. This causes joints between both rim
elements to appear on a front side of the rim section which is
observable from a driver's seat and a rear side thereof which is
30 not observable from the driver's seat. Thus, when it is desired
to improve aesthetic properties of the rim section and therefore
the steering wheel, it is merely required to cover the front side
joint with a molding or the like.

In a preferred embodiment of the present invention, the

mounting step includes mounting a cover member, such as a molding, an ebony-patterned member, or the like on a joint between the rim elements. This not only effectively hides the joint but provides the steering wheel with a decorative effect. Also, it permits joining between the rim elements to be strengthened.

In a preferred embodiment of the present invention, the thermosoftening synthetic resin material which is fed in the extruding step is constituted by a combination of pellets having ~~the~~ woodmeal ~~kneadingly~~ incorporated therein ^{BY KNEADING} and pellets having a color pigment added thereto as well as the woodmeal and exhibiting a color different from that of the former pellets. This permits mass-production of a steering wheel which gives the impression that it is formed thereon with a woodgrain pattern as if it is formed by a sliced veneer.

In a preferred embodiment of the present invention, the method further includes the step of applying a coating to the rim elements ^{wherein} the coating is applied to a front side of the rim elements observable from a driver's seat. This minimizes a stain on the front side of the rim section while preventing the feel of wood on the rear side thereof from being deteriorated.

In a preferred embodiment of the present invention, the method further includes the step of carrying out liquid pressure transfer printing of the rim elements, wherein the transfer print is applied to a front side of the rim elements observable from a driver's seat. Also, the liquid pressure transfer printing is carried out so as to permit formation of a transfer printing pattern by gradations on the rim elements, wherein a transfer ink layer is gradually reduced in thickness toward a rear side of the rim elements ^{so that} whereby a ground pattern gradually appears on the rim elements.

This minimizes a stain of the front side of the rim section while preventing the feel of wood on the rear side from being deteriorated. Also, it permits the flow pattern and

transfer pattern to cooperate with each other to provide the rim section with a high-grade appearance which gives the impression of a pretty grain pattern of precious wood.

5

BRIEF DESCRIPTION OF THE DRAWINGS

These and other objects and many of the attendant advantages of the present invention will be readily appreciated as the same becomes better understood by reference to the following detailed description when considered in connection with the accompanying drawings; wherein:

10

Fig. 1A is a perspective view showing an embodiment of a steering wheel according to the present invention;

Fig. 1B is a fragmentary sectional view of the steering wheel of Fig. 1A taken along line 1B-1B;

15

Fig. 2A is a schematic view showing steps in a method for manufacturing a steering wheel according to the present invention by way of example;

Fig. 2B is an enlarged sectional view of part 2B in Fig. 2A;

20

Fig. 3A is a schematic view showing a liquid pressure transfer printing step in a method for manufacturing a steering wheel according to the present invention by way of example;

Fig. 3B is a plan view showing rim elements mounted on a carrier unit;

25

Figs. 4A to 4C are schematic views showing a liquid pressure transfer printing step which permits formation of a transfer printing pattern by gradations, respectively;

30

Figs. 5A and 5B each are an enlarged sectional view showing a rim element which has been subjected to liquid pressure transfer printing, to thereby be provided thereon with the transfer printing pattern by gradations;

Fig. 6 is a sectional view of a die for extruding rim elements for a rim section, showing a configuration of a nozzle provided on the die;

Fig. 7A is a side elevation view partially in section showing another embodiment of a steering wheel according to the present invention;

Fig. 7B is an exploded sectional view of part 7B in Fig. 7A; and

Fig. 7C is an exploded sectional view showing another arrangement similar to that of Fig. 7B.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Now, the present invention will be described hereinafter with reference to the accompanying drawings. The following description will be first made on a steering wheel according to the present invention. Then, manufacturing of the steering wheel of the present invention will be described. In the following description, a starting material of which a rim section for the steering wheel is made will be referred to as a raw material A0, a straight rod-like member formed of the raw material A0 by extrusion will be referred to as a straight rim element A1, and an arcuate member formed by bending the rim element A1 will be referred to as an arcuate rim element A2.

Referring first to Figs. 1A and 1B, an embodiment of a steering wheel according to the present invention is illustrated. A steering wheel of the illustrated embodiment which is generally designated by reference numeral 1 generally includes a boss section 2 acting as a center of rotational movement of the steering wheel 1, spoke sections 3 arranged so as to radially extend from the boss section 2, and a rim section 4 connected to a distal end of each of the spoke sections 3 and formed to have an annular shape. The rim section 4 is constituted by a long rim portion 41 of an elongated arcuate shape (positioned on an upper side in Fig. 1A), a short rim portion 42 of a short arcuate shape (positioned on a lower side in Fig. 1A), and two grip portions 43 (positioned on both lateral sides in Fig. 1A) for connecting the long rim portion 41 and short rim portion 42 to each other

therethrough. The rim section 4 has a core 44 incorporated therein, which may be formed by bending a metal rod into an annular shape, by way of example. The long rim portion 41, short rim portion 42 and grip portions 43 are mounted on the core 44, to thereby provide the rim section 4. In the illustrated embodiment, the spoke sections 3 may be made of metal and welded directly to the core 44, so that the grip portions 43 may be formed of flexible urethane by insert molding so as to extend over both core 44 and spoke sections 3. Then, the long rim portion 41 and short rim portion 42 are mounted on the core 44 on which the grip portions 43 are thus molded, resulting in a so-called combination steering wheel being provided. Alternatively, the grip portions 43 may each be mounted therein with a rim element A2 of an arcuate shape.

In the illustrated embodiment, the long rim portion 41 and short rim portion 42 are each constituted by two halves formed so as to extend in a longitudinal direction thereof, resulting in interposedly hold the core 44 therebetween. The two halves are adhesively joined to each other to provide each of the long rim portion 41 and short rim portion 42. More specifically, supposing that the long rim portion 41 and short rim portion 42 are mounted in a vehicle, a front side member of the long rim portion 41 which is observable from a driver's seat is designated by reference character 41a and that of the short rim portion 42 observable therefrom is 42a. Also, rear side members of the long rim portion 41 and short rim portion 42 which are not observable from the driver's seat or are out of sight of the driver are designated by reference characters 41b and 42b, respectively. The front and rear side members 41a and 41b of the long rim portion 41 are each formed to have a substantially semicircular shape in section by way of example. This is true of the front and rear side members 42a and 42b of the short rim portion 42. The front and rear side members of the long and short rim portions 41 and 42 are each formed at a central portion thereof

with a core holding recess 45 in a manner to extend ^{EXTENDING} in a longitudinal direction thereof. Thus, in the illustrated embodiment, the long ^{FIRST} rim portion 41 and short ^{SECOND} rim portion 42 are each constituted by the two front and rear side members joined to each other. Alternatively, the long and short rim portions 41 and 42 may be configured as shown in Fig. 5B. More specifically, in Fig. 5B, the front side members ^(FIRST RIM ELEMENTS) 41a and 42a of the long and short rim portions 41 and 42 are each formed to have a ^(i.e., HAVE A LONGITUDINAL NOTCH THEREIN) substantially C-shape in section, so that the core 44 is received therein from a side of a rear surface thereof. Also, the rear side members ^(SECOND RIM ELEMENTS) 41b of the long rim portion 41 and the rear side member ^(SECOND RIM ELEMENT) 42b of the short rim portion 42 are each formed to have a thickness substantially equal to a ^{DIA METER} thickness of the core 44, to thereby close the core holding recess 45.

Further, in the illustrated embodiment, it ^{is not} ~~is~~ ^{BE FORMED} necessarily required that the rim section 4 ~~is constituted of~~ ^{also} each front and rear side members as described above. It may be configured as shown in Figs. 7A and 7B. More particularly, the long ^{FIRST} rim portion 41 is constituted of two halves ^(or) an inner peripheral side member 41c and an outer peripheral side member 41d) and the short ^{SECOND} rim portion 42 is constituted of two halves ^(or) an inner peripheral side member 42c and an outer peripheral side member 42d. Such configuration of Figs. 7A and 7B causes joints between the inner peripheral side member 41c (42c) and the outer peripheral side member 41d (42d) to appear on both a front position observable from the driver's seat and a rear position out of sight of the driver. Thus, a cover member 46 such ^a ~~a~~ molding, an element formed thereon with an ebony-like pattern or the like may be attached to at least the front joint to hide it from view. Such attachment of the cover member 46 to the ^{FORMED} ~~joints~~ may be likewise applied to the rim section 4 ~~constituted of~~ of the front side member and rear side member as described above. Attachment of the cover member 46 to the joints of the rim section 4 may be carried out by forming each of the inner and outer peripheral

side members or front and rear side members with a recess and interposedly fitting both ends of the cover member 46 formed to have a substantially C-shape into the respective recesses of the side members. This also ensures reinforcement of the rim section 4. In Figs. 7A to 7C, reference numerals 41e, 41f, 42e and 42f designate non-slip holding unevenness formed on the rear side of the rim section 4.

Now, a raw material A0 for the long rim portion 41 and short rim portion 42 will be described. The raw material A0 essentially consists of a thermoplastic or thermosoftening synthetic resin material such as AAS (acrylonitrile acrylic styrene) resin, AES (acrylonitrile-(ethylene-propylene-diene terpolymer)-styrene) resin, ABS (acrylonitrile butadiene styrene) resin or the like. In addition to the synthetic resin material, the raw material A0 contains woodmeal in an amount of tens of percent added to the resin material. By way of example, the raw material may be constituted by AAS (acrylonitrile acrylic styrene) resin acting as a main component and woodmeal of 60 μ m in average particle diameter in an amount of 20% which has an inorganic pigment such as titanium oxide or the like incorporated therein.

The woodmeal referred to herein includes not ~~a mere~~ ^{merely} wood powder (wood shavings) but ~~a mixture of the woodmeal~~ ^{woodmeal} with an inorganic pigment such as titanium oxide, iron oxide, cadmium yellow, carbon black or the like added thereto so as to permit the woodmeal to withstand an elevated temperature during the molding. For this purpose, a product commercially available under "TECHNOMATERIAL" (trademark) from MISAWA HOMES CO., LTD. may be suitably used. When such woodmeal having titanium oxide incorporated therein is kneaded into the main component or synthetic resin material, the raw material exhibits a color within a range between light brown and a flesh color, because titanium oxide has a white color. Also, addition of the woodmeal having iron oxide or an inorganic pigment such as cadmium yellow,

carbon black or the like incorporated therein^{to} the synthetic resin material permits the raw material to exhibit a different appearance^{IN} color, such as dark brown or the like, because the iron oxide or the inorganic pigment has a color other than a white color.

5 The amount of each of the synthetic resin material and woodmeal added thereto may be suitably varied depending on various conditions such as molding conditions, ^{THE} a type of ~~the~~ synthetic resin material used, compatibility with the synthetic resin material or the inorganic pigment, and the like.

10 Now, manufacturing of the steering wheel 1 thus constructed will be described with reference to a manufacturing process 10 shown in Fig. 2A. The process 10 generally includes an extruding step 11, a bending step 13 and a rim assembling step 14. Also, the process 10 includes a thermally softening step 12 practiced as a pretreatment prior to the bending step 13. In addition, the process 10 may optionally include a liquid pressure transfer printing step 15 and the like.

15 In the extruding step 11, the raw material A0^(I.E., SYNTHETIC RESIN MATERIAL AND WOODMEAL) is melted by heating in a cylinder of an extruding machine or the like known in the art and then extruded through a die nozzle or a forming die, resulting in the straight rim element A1 ~~which has a~~ ^{HAVING THE CROSS-SECTIONAL} desired V-shape ~~in cross-section~~ being obtained. Feeding of the raw material A0 to the extruding machine is not carried out in such a manner that the synthetic resin material and woodmeal are fed at a predetermined compounding ratio directly to the extruding machine. Rather, pellets formed by kneading the synthetic resin material and woodmeal with each other are fed to the extruding machine. Desirably, plain-colored pellets made of

20 25 30 "TECHNOMATERIAL" constituted by incorporating titanium oxide into woodmeal and colored pellets made of "TECHNOMATERIAL" constituted by incorporating a color pigment into the woodmeal so as to exhibit a brown color are fed at a compounding ratio of 3:1 to the extruding machine. When the pellets thus fed to the

extruding machine are extruded from the extruding machine while being kept from being completely uniformly mixed together, a streak-like flow pattern ^{IN} ~~ON~~ which light and shade alternately appear is ~~permitted to be~~ formed in a straight streak-like manner on the straight rim element A1. Of course, use of either the plain-colored pellets or the colored pellets likewise permits a straight streak-like ^(STREAKED) flow pattern to be somewhat formed on the straight rim element A1, because the woodmeal is a natural material. ^{THUS, THE WOODMEAL PELLETS ARE BEING} ~~to thereby be kept from fully~~ homogenized in the resin material, and the pellets ^{ARE} ~~is~~ extruded from the extruding machine under an extrusion pressure of the machine. The flow pattern thus formed creates a woodgrain pattern such as a straight grain pattern or a cross grain pattern, to thereby permit the rim element A1 to exhibit an appearance of wood.

In the illustrated embodiment, the straight rim element A1 constitutes the front side member 41a and rear side member 41b of the long rim portion 41 and the front side member 42a and rear side member 42b of the short rim portion 42 later. The straight rim element A1 may be formed to have a substantially semicircular shape in section of which a central portion is recessed. ^(IE, ELEMENT A1 INCLUDES A CENTRAL LONGITUDINAL GROOVE) More specifically, as shown in Fig. 6, the straight rim element A1 is desirably extruded by means of a forming die or a die 16 projectingly provided with a nozzle ^{OUTER} formed to have a configuration in section including an arcuate section 16a which substantially conforms to an arcuate shape in section obtained by dividing the thickest portion (outermost portion) of the long rim portion 41 or short rim portion 42 of a finished steering wheel into a front side half and a rear side half. ^{THE DIE ALSO INCLUDES} ~~as well as a~~ chord section 16b which is projectingly provided with a core ^(INNER ARCULATE) corresponding section 16c formed to have a configuration substantially conforming to a half of a sectional configuration of the core 44. When the straight rim element A1 is thus formed by extrusion using the nozzle-equipped die 16 or the forming die, ^{DISTORTION OR MISALIGNMENT} ~~disorder or disturbance~~ of the flow pattern which contributes to

creation of a woodgrain pattern such as a straight grain or a cross grain is minimized during the subsequent re-shaping step. PATTERN

Fig. 6 shows a section of the die provided with the nozzle for extrusion of the rear side members 41b and 42b which are substantially out of sight of the driver. Of course, it is possible to roughly form such a sectional configuration by means of a die nozzle and then finely form the sectional configuration by means of a forming die. PATTERN

In the thermally softening step 12, the straight rim element A1 for the front and rear side members 41a and 41b of the long rim portion 41 and the front and rear side members 42a and 42b of the short rim portion 42 which has been thus prepared in the extruding step 11 is received in, for example, a thermostatic oven 17, ~~or the like, wherein~~ the straight rim element A1 is heated to a temperature of about 100 to 120°C, resulting in the rim element A1 being softened. When the preceding extruding step 11 and subsequent bending step 13 are carried out at the same treatment speed, the rim element A1 immediately after extruded in the extruding step 11 still holds softness to a degree, so that it may be transferred directly to the bending step 13 without being subjected to the thermally softening step 12. However, in view of a difference in treatment speed between the preceding extruding step 11 and the subsequent bending step 13 and efficient operation ~~of whole~~ all of the equipment, it is desirable that the rim elements A1 as extruded from the extruding step 11 are permitted to be solidified by cooling while being kept in a straight rod-like shape, and then cut to a predetermined even length or collected in a predetermined lot size, followed by feeding to the bending step 13. In this instance, the rim element A1 once solidified in the straight rod-like shape is exposed to the thermally softening step 12, resulting in the rim element A1 being softened to a degree which permits it to be re-shaped in the subsequent step. A heating temperature and a period of heating time each may be merely set at a level which being

permits re-shaping of the rim element A1. Excessive heating of the rim element ~~loses meaning~~ ^{PREVENTS THE NECESSITY} of using the above-described die provided with the nozzle of a fine configuration.

5 In the bending step 13, the rim element A1 kept softened is subjected to re-shaping, resulting in the rim element A1 being transformed from the straight rod-like shape into an arcuate shape conforming ^{TO} a curvature of the core 44. In the illustrated embodiment, in the bending step 13, the straight rim element A1 kept softened is roughly bent into an arcuate shape by hand.

10 Then, the rim element A1 is fitted in a regulating die 18 and ~~then~~ a forcing die 19 is forced against the regulating die 18, resulting in forming the arcuate rim element A2. The regulating die 18 and forcing die 19 are so configured that a cavity formed by cooperation of the dies 18 and 19 is formed ^{FIRST} to have the same

15 sectional configuration as that of the long rim portion 41 or short ^{SECOND} rim portion 42 of a finished steering wheel. Removal of the arcuate rim element A2 from the dies 18 and 19 is desirably carried out after it ^{HAS} solidified to a degree by cooling. For this purpose, the dies may be provided with any suitable heating

20 and cooling means. Thus, removal of the rim element A2 from the dies is carried out so as to prevent deformation of the rim element after ~~the~~ removal while taking manufacturing efficiency into consideration.

In general, a steering wheel is formed on a rear side thereof with non-slip ^{SURFACE} holding unevenness for facilitating holding of the steering wheel. In the illustrated embodiment, formation of such ^{SURFACE} holding unevenness A2a may be carried out simultaneously ^{WHILE} with re-shaping ~~of~~ the rim element into a general arcuate configuration during the bending step 13 ^{TO TRANSFORM} ~~wherein~~ the straight rim element A1 ~~is transformed~~ into the arcuate rim element A2.

30

In the bending step 13, transformation of the straight rim element A1 into the arcuate rim element A2 causes ^{Flow} ~~flowing~~ of the material due to some difference in three-dimensional geometric volume between the straight rim element A1 and the

arcuate rim element A2. Also, formation of the non-slip ^{CROSS-} unevenness A2a described above causes a variation in section of the rim element, leading to flow of the material. Thus, in order to ensure that the flow pattern which contributes to creation of a woodgrain pattern ^{PATTERN} such as a straight grain ^{CROSS-} or a cross grain ^{PATTERN} is prevented from being ^{DISTORTED} ~~disordered~~ by the material flow, the illustrated embodiment is so configured that the arcuate cavity defined by cooperation between the regulating die 18 and the forcing die 19 provides a room region 20 on each of opposite ends defined in a longitudinal direction thereof, to thereby permit the material to escape to the room regions 20. Also, in the illustrated embodiment, the regulating die 18 formed with projections 18a for forming the non-slip ^{SURFACE} unevenness A2a on the rim element A2 is used for pressing the arcuate rim element A2 which is configured to conform to the arcuate shape in section obtained by dividing the thickest portion (outermost portion) of the long ^{FIRST} rim portion 41 or short ^{SECOND} rim portion 42 of a finished steering wheel into the front side half and rear side half. Thus, the ~~resulting~~ unevenness A2a is formed by merely forcing the projections 18a of the regulating die 18 against the rim element, to thereby minimize disorder of the flow pattern.

Thus, the bending step 13 permits the straight streak-like flow pattern formed on the straight rim element A1 in the extruding step 11 to be transformed into an arcuate flow pattern along the arcuate configuration of the arcuate rim element A2 without being ^{DISTORTED.} ~~disordered~~, ^{THEREFORE,} ~~so that~~ the rim element A2 may exhibit an appearance of wood created by the woodgrain pattern.

An assembly preparation step may be carried out before the arcuate rim element A2 thus bent is mounted on the core 44. More specifically, for example, when the arcuate rim element A2 for each of the long ^{FIRST} rim portion 41 and short ^{SECOND} rim portion 42 is formed to have a length larger than a predetermined one in the preceding step, the assembly preparation step is carried out in order to cut it into the predetermined length. Also, the step

may be carried out for making edges of the rim element thus cut uniform or subjecting an arcuate surface of the rim element to light grinding. Further, ~~it may take place for applying a~~ MAY BE APPLIED a coating such as a clear coating or the like to the surface of the rim element. The surface grinding permits removal of a skin layer which tends to be formed on the surface of the rim element therefrom, to thereby expose the woodmeal, so that the finished product or steering wheel 1 may exhibit the feel of wood. Of course, when a coating such as a clear coating is applied to the whole steering wheel 1, applying of the coating is not carried out in the assembly preparation step. Instead, applying of the coating may be practiced after the rim assembling step of mounting the element A2 on the core. In the assembly preparation step, the coating on the rim element A2 for each of the long rim portion 41 and short rim portion 42 permits the front side thereof to have been burnished and the rear side thereof to be kept exhibiting the feel of wood. THE COATING IS ONLY APPLIED TO THE FRONT SIDES. PERFORMED

The rim assembling step 14 briefly described above is to mount pairs of the arcuate rim elements A2 bent into an arcuate shape on the core 44 while interposing the core 44 between the rim elements A2. In the illustrated embodiment, the front side member 41a and rear side member 41b of the long rim portion 41 are joined to each other and to the core 44 by means of an adhesive applied to the chord section 16b and core corresponding section 16c thereof. Likewise the front side member 42a and rear side member 42b of the short rim portion 42 are joined to each other and to the core 44 using the adhesive. The front side members and rear side members are kept clamped until adhesive joining therebetween is attained. Then, a portion of the adhesive projecting from between the members and solidifying is removed by grinding, resulting in the finished steering wheel 1 being obtained.

In the steering wheel 1 thus manufactured, the flow pattern on each of the long rim portion 41 and short rim portion

42 each constituted by the rim elements A2 may be observed in the form of an annular flow pattern extending along an annular configuration of the steering wheel, so that light and shade alternately appear in the flow pattern. This permits a woodgrain pattern giving the impression that it is formed by a sliced veneer to appear on the steering wheel 1, so that it may satisfactorily exhibit an appearance of wood.

In the illustrated embodiment, the rim section 4 of the steering wheel 1 is divided into the front side and rear side, each of which is constituted by the rim element A2. Such construction permits joints between the front side member and the rear side member to be positioned at the innermost peripheral portion of the rim section 4 and the outermost peripheral portion thereof, resulting in the joints being conveniently out of sight of a driver. In general, such joints are fine ~~to a degree of~~ *IN THAT* ~~rendering it~~ *THEY ARE* substantially impossible to recognize ~~at~~ at a glance. However, in order to hide the joints and provide a specific decoration effect, the cover member 46 such as a molding, an ebony-patterned element or the like may be mounted thereon. In this instance, the illustrated embodiment, as shown in Fig. 7C, may be so configured that the rim elements for the front side member and rear side member are formed with recesses, respectively, and the cover member 46 of a C-shape is securely mounted on the joint while both ends of the cover member 46 are fitted in the respective recesses of the rim elements. Attachment of the cover member 46 to the rim elements A2 may be attained by any suitable means such as welding, fusion bonding, fitting or the like in addition to an adhesive. Mounting of the cover member 46 on the joints between the rim elements is advantageous when the rim section 4 is constituted by the inner peripheral side member and outer peripheral side member.

The liquid pressure transfer printing step 15 may be optionally practiced as required, like the clear coating step. The liquid pressure transfer printing step 15 may be carried out

on the whole steering wheel which has been just subjected to the rim assembly step of mounting the long rim portion and short rim portion on the core. Alternatively, it may be carried out on the arcuate rim element A2 which has been subjected to the bending step. The following description will be made ^{of} ~~on~~ liquid pressure transfer printing carried out on the arcuate rim element A2.

^{USING} ~~means of~~ The liquid pressure transfer printing may be practiced ~~by~~ a liquid pressure transfer apparatus designated by reference numeral 30 in Fig. 3A. The liquid pressure transfer apparatus 30 generally includes a transfer bath 31, a transfer film feed unit 32 and an object carrier unit 33. The transfer bath 31 is fed therein with a transfer film F on which a suitable pattern such as a woodgrain pattern or the like is printed by means of the transfer film feed unit 32. The transfer film F thus fed to the transfer bath 31 is ~~kept~~ floated on a surface of a liquid in the bath 31. When the transfer film F is activated, resulting in it being rendered transferable, the object carrier unit 33 is actuated to force an object W ^(to which an ink pattern on the transfer film F is to be transferred) against the transfer film F, so that the ink pattern on the transfer film F may be transferred to the object W. In this instance, the object W is constituted by the arcuate rim element A2 for each of the front side members 41a and 42a constituting the front side of the rim section 4 of the steering wheel 1.

In Fig. 3A, ^{into} ~~the~~ the object W is shown as if it is vertically downwardly lowered ~~into~~ the transfer bath 31. Alternatively, the object W may be obliquely lowered by means of a conveyor of an inverted triangular configuration or a robot. Also, in the illustrated embodiment, the transfer film F is coated thereon with an activator and then fed to the transfer bath 31.

Alternatively, the illustrated embodiment may be so configured that the transfer film F is fed to the transfer bath 31 and then coated thereon with a solvent or the like, ^{the} ~~resulting~~ resulting in the transfer film F being activated. Further, ^{the} ~~in~~ illustrated

embodiment, the transfer film F is continuously fed to the transfer bath 31 in which the liquid ~~is~~ flows. Alternatively, individual transfer films F, which are in the form of a leaf, may be fed one by one by hand to the transfer bath 31 in which the liquid is kept stationary and then the object W is immersed in the liquid by hand. In addition, the object W is constituted by the arcuate rim element A2. The object W may be the straight rim element A1 which is not subjected to the bending step 13, as shown in Fig. 3B.

10 The liquid pressure transfer printing ~~is~~ desirably proceeded while permitting a transfer ink layer Q to be gradually reduced in thickness. For this purpose, a plurality of the objects W may be forcedly immersed in the liquid while being spaced from each other at predetermined intervals, as shown in
15 Figs. 4A to 4C by way of example. This permits the transfer film F to be gradually reduced in thickness toward a chord of a section of the rim element A2. The transfer film F is ultimately cut near both ends of an arc of the rim element A2, resulting in a transfer printing pattern being formed by gradations on the rim
20 element A2, wherein a ground pattern gradually appears on the rim element A2. In Figs. 3A and 3B, reference numeral 34 designates film extension members formed to have substantially the same configuration as the objects W and arranged on both sides of the objects W.

25 When the liquid pressure transfer printing is to be carried out on a single object W or on the whole steering wheel which has been subjected to the rim assembling step, the film extension member 34 may be formed to have, for example, a screen-like configuration while being spaced from the object W at a
30 substantially uniform interval outside an outer periphery of the object W. Such liquid pressure transfer printing may be carried out according to a procedure disclosed in Japanese Patent Application Laid-Open Publication No. 117326/1995 entitled "Liquid Pressure Transfer Method", of which the disclosure is

herein incorporated by reference.

Also, in the illustrated embodiment, the liquid pressure transfer printing is carried out on the rim element A2 for each of the front side members 41a and 42a of the long and short rim portions 41 and 42. The liquid pressure transfer printing may be carried out on the whole steering wheel which has been subjected to the rim assembling step 14. In this instance, the liquid pressure transfer printing, of course, can be made on the rear side members 41b and 42b of the long and short rim portions 41 and 42 which are hard to be observed from a driver's seat as well. When the transfer printing takes place on a whole periphery of the steering wheel, a joint between both ends of the transfer film F is desirably located at a position which permits the joint to be out of sight of a driver's seat. Such liquid pressure transfer printing may be practiced according to a procedure disclosed in Japanese Patent Application Laid-Open Publication No. 329498/1998 entitled "Method for Manufacturing Steering Wheel Having Liquid pressure Transfer Printing Applied Thereto", of which the disclosure is herein incorporated by reference.

The liquid pressure transfer printing step 15, as shown in Fig. 5A, permits the print to be exclusively applied to the front side members 41a and 42a of the long and short rim portions 41 and 42 which are observable from a driver's seat in a state where the steering wheel 1 is mounted in a vehicle. Also, in the illustrated embodiment, the step 15 permits formation of the transfer printing pattern by gradations wherein the transfer ink layer Q is gradually reduced in thickness toward the innermost and outermost peripheral portions of the rim section 4, resulting in the ground pattern gradually appearing. On the front side of the steering wheel 1 which is observable from a driver's seat, the flow pattern acting as the ground pattern is observed through the transfer pattern superposed on the ground pattern, so that the flow pattern or ground pattern and the transfer pattern synergistically cooperate with each other to create a woodgrain

pattern. The thus-created woodgrain pattern is rendered gradually thin toward the rear side of the steering wheel which is out of sight of a driver. Whereas, the feel of wood on the rear side of the steering wheel is not deteriorated, resulting in the feel being substantially equal to that of natural wood.

In the illustrated embodiment, the joint or boundary region of the transfer pattern is defined at each of the innermost peripheral portion and outermost peripheral portion of the rim section 4. When the front side members 41a and 42a of the long and short rim portions 41 and 42 which constitute the front side of the steering wheel 1 are formed to have a C-shape in section as shown in Fig. 5B or when the liquid pressure transfer printing is carried out on the whole steering wheel which has been subjected to the rim assembling step 14, the boundary may be defined at a more rearward position.

Although the method of the present invention has been described above as related to the embodiments of a steering wheel, the method may be used for manufacturing an article for a vehicle having a flat shape, such as a cover plate for a power window switch or the like. For providing such an article, an extruded plate is subjected to re-heating, rough bending, fitting in a die, ^{and} pressing ~~and the like in turn~~ in a similar manner as described above.

While preferred embodiments of the invention have been described with a certain degree of particularity with reference to the drawings, obvious modifications and variations are possible in light of the above teachings. It is therefore to be understood that within the scope of the appended claims, the invention may be practiced otherwise than as specifically described.

ABSTRACT OF THE DISCLOSURE

15
HAS A steering wheel capable of giving the impression that it
formed thereon with a woodgrain pattern in a manner to extend
in a circumferential direction thereof, resulting in the steering
5 wheel having both an appearance and feel of wood which is
substantially equal to that of natural wood. The steering wheel
includes a rim section having a core incorporated therein. The
rim section is constituted by rim elements made of a
thermosoftening synthetic resin material to which woodmeal is
10 added, resulting in the rim section being formed thereon with a
streaked flow pattern. The rim elements are each re-shaped from a
straight rod-like configuration into an arcuate configuration so as to
conform to a curvature of the core and are mounted on the core, so
15 that the flow pattern may be transformed into an annular flow
pattern.